

TECHNICAL DATA SHEET: FB NIPPLE TO GO OVER

Ø mm	I/D mm	Flat Edge mm	Steel Thickness mm	Weight kg
80	83	6	0,7	0,2
100	103	6	0,7	0,3
120	123	6	0,7	0,4
125	128	6	0,7	0,4
140	143	6	0,7	0,5
150	153	6	0,7	0,5
160	163	6	0,7	0,6
180	183	6	0,7	0,6
200	203	6	0,7	0,7
225	228	6	0,7	0,7
250	253	6	0,7	0,8
300	303	6	0,7	0,9
315	318	6	0,9	1,0
350	353	6	0,9	1,1
400	403	6	0,9	1,3
450	453	6	0,9	1,5
500	503	6	0,9	1,6
550	553	6	0,9	1,8
600	603	6	0,9	1,9



Construction:

Ends: 6 mm turned out edge (FB).

Additional Notes

At temperatures ranging between 200° C and 250° C, the zinc-iron alloy layers in galvanised steel will continue to provide a high level of protection from corrosion. However, there may be some peeling, changes in mechanical properties, and reduction in the corrosion protection. Recommended max. service temperature is +80°C.

304SS available upon request.

Compliance / Rating of Product Components

Product	Material	Compliance / Rating
FB Nipple to go over	Galvanised 304 Stainless Steel	DX51D with Z275 Coating EN.1.4301/TP.304
Joka Seal Metal Sealant 2315	Aceton Blend	AAMA Specification 801.1

Temperature Rating of Product Components

	FB Nipple to go over	Sealant
593°C		
200°C		
121°C	Galvanised Steel	304 Stainless Steel
-20°C		Joka Seal Metal Sealant 2315

