

TECHNICAL DATA SHEET: QUICK-FIT (QF) ROOF PLATE

Ø mm	Plate Width mm	Plate Length mm	Steel Thickness mm	Weight kg
100	412	412	0,7	2,4
125	437	437	0,7	2,5
140	452	452	0,7	3,2
150	462	462	0,7	3,5
160	472	472	0,7	3,8
180	492	492	0,7	3,9
200	512	512	0,7	4,2
250	562	562	0,7	4,9
315	627	627	0,7	5,1
350	662	662	0,7	5,7
400	712	712	0,9	7,3
450	762	762	0,9	8,1
500	812	812	0,9	9,0
560	782	782	0,9	10,2
630	942	942	0,9	11,4
710	1022	1022	0,9	12,7
800	1112	1112	0,9	14,9
900	1212	1212	0,9	17,2
1000	1312	1312	0,9	19,2



Additional Notes

At temperatures ranging between 200° C and 250° C, the zinc-iron alloy layers in galvanised steel will continue to provide a high level of protection from corrosion. However, there may be some peeling, changes in mechanical properties, and reduction in the corrosion protection. Recommended max. service temperature is +80°C. Stainless Steel available upon request.

Compliance / Rating of Product Components

Product	Material	Compliance / Rating
Quick-Fit (QF) Roof Plate	Galvanised 304 Stainless Steel	DX51D with Z275 Coating EN.1.4301/TP.304
Joka Seal Metal Sealant 2315	Aceton Blend	AAMA Specification 801.1

Temperature Rating of Product Components

	Quick-Fit (QF) Roof Plate	Sealant
593°C		
200°C		
121°C	Galvanised Steel	304 Stainless Steel
-20°C		Joka Seal Metal Sealant 2315

